



## Technical Information and Typical Properties

### ECOSUPREME 2 Prestretched Hand Film .33 mil




---

#### Product Description

ECOSUPREME and ECOSUPREME 2 are Sigma Stretch Film’s newest, premium grade stretch films made with special orientation that produces stronger film at thinner gauges. Core extensions and ultra-light weight rolls make ECOSupreme easy to handle and reduce wrapper fatigue. Engineered to outperform all competitive hand films — regardless of gauge — ECOSUPREME has reinforced edges to provide unrivaled load-holding force and tear resistance. ECOSUPREME’s aggressive cling package is strong enough for B and many C loads. Low case prices and on-the-load cost make ECOSUPREME ECO-nomical. And, using less film per load makes ECOSUPREME — ECO-friendly!

---

#### General

Applications

Cold environments; Grocery warehouse; Internal wrapping; Boxed products; Food processing; All load profiles

Revision Date      4/20/2016      Available in widths from 13"-18"

Film Properties	Typical Value		
	(English)	Tolerance	Test Method
Tensile Strength at Yield MD	No Yield	± 15%	ASTM D882
Tensile Strength at Yield TD	1000psi	± 15%	ASTM D882
Tensile Strength at Break MD	15000psi	± 15%	ASTM D882
Tensile Strength at Break TD	4000psi	± 15%	ASTM D882
Elongation at Break MD	180%	± 15%	ASTM D882
Elongation at Break TD	690%	± 15%	ASTM D882
Protrusion Puncture	5.3 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	12.5 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	450 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	980 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

---

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	8.4 micron	

---

#### Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: [Sigma.Stretch@sigmaplastics.com](mailto:Sigma.Stretch@sigmaplastics.com)

Visit our website at [www.sigmastretchfilm.com](http://www.sigmastretchfilm.com)

©Copyright 2015 MSC Marketing & Technology, Inc.