



Technical Information and Typical Properties

MSC Two Side-Cling Machine Film .80 mil



Product Description

Select is Sigma's most versatile cast machine film. This robust, all purpose engineered cast film is ideal for medium speed applications, while still providing outstanding containment levels.

General

Applications •High volume • Lower speed wrapping •One side-cling not required
Revision Date 6/22/2015 Available in 20 and 30 inch widths

Film Properties	Typical Value		Test Method
	(English)	Tolerance	
Tensile Strength at Yield MD	1300 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1200psi	± 15%	ASTM D882
Tensile Strength at Break MD	6900psi	± 15%	ASTM D882
Tensile Strength at Break TD	4000psi	± 15%	ASTM D882
Elongation at Break MD	480%	± 15%	ASTM D882
Elongation at Break TD	620%	± 15%	ASTM D882
Protrusion Puncture	10.0 lbs	± 15%	ASTM D5748
Protrusion Puncture Energy	23.0 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	330 g/mil	± 15%	ASTM D1922
Elmendorf Tear Strength TD	540 g/mil	± 15%	ASTM D1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05 in
Film Thickness	20.3 micron	

Manufactured with pride in the USA and Canada by

Sigma Stretch Film

Page & Schuyler Aves. Bldg #8

Phone: 800-672-9727 • 201-507-9100

Email: Sigma.Stretch@sigmaplastics.com

Visit our website at www.sigmastretchfilm.com

©Copyright 2015 MSC Marketing & Technology, Inc.