



## Product Data Sheet

### PLATINUM MAX MACHINE FILM

| Property                      | Highlight Method   | Value            |
|-------------------------------|--------------------|------------------|
| <b>THICKNESS</b>              | <b>GAUGE (MIC)</b> | <b>55 (14.0)</b> |
|                               |                    |                  |
| <b>ELMENDORF TEAR (GRAMS)</b> | <b>D-1922</b>      | <b>285</b>       |
| <b>ELMENDORF TEAR (GRAMS)</b> | <b>D-1922</b>      | <b>410</b>       |
| <b>ULTIMATE TENSILE (PSI)</b> | <b>D-882</b>       | <b>7,390</b>     |
| <b>ULTIMATE TENSILE (PSI)</b> | <b>D-882</b>       | <b>5,680</b>     |
| <b>MAXIMUM ELONGATION (%)</b> | <b>D-882</b>       | <b>697%</b>      |
| <b>MAXIMUM ELONGATION (%)</b> | <b>D-882</b>       | <b>808%</b>      |
| <b>DART DROP (GRAMS)</b>      | <b>D-1709</b>      | <b>206</b>       |
| <b>GLOSS 45 (%)</b>           | <b>D-2457</b>      | <b>89</b>        |
| <b>HAZE (%)</b>               | <b>D-1003</b>      | <b>1.4</b>       |

NOTE: The data presented above are nominal values for the product type described and must not be construed as specifications. Therefore no guaranty expressed or implied. Data will be tested to a +/- 10% standard deviation